



JX ALTA™ HP

High Perm Breathable Housewrap

Properties Data Sheet

ESR - #1108

Physical Properties		Test Method	JX ALTA™ HP
Basis weight, gsm		ASTM D 3776	72
Thickness, mils		ASTM D 3776	8
Gurley Air Porosity, sec.		TAPPI T-460	> 1800
Water Resistance, cm		AATCC 127	>250
1" tensile, lbs	MD	ASTM D 882	30
	CD		30
Trapezoid Tear, lbs	MD	ASTM D-1117	14
	CD		11
MVTR	Perms	ASTM E-96, method A	66
UV Light Exposure		Aging Test	4 Months
Drainage Efficiency test		ASTM - 2273	>95%
Flammability		ASTM - E-84	Class A

Roll Dimensions (ft.)	W x L	9' X 100'	9' X 150'
		10' X 100'	10' X 150'

The information contained herein is furnished without charge or obligation and the recipient assumes all responsibility for its use. Because conditions of use and handling may vary and are beyond our control, we make no representation about, and are not responsible or liable for, the accuracy or reliability of said information or the performance of any product. Any specifications, properties or applications listed herein are provided as information only and in no way modify, amend, enlarge or create any warranty. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent. CLAF® is a registered trademark of JX Nippon ANCI Corporation.

02/16