



JX ALTA™ PRIME

Perforated Housewrap

Properties Data Sheet

ESR - #3784

Physical Properties		Test Method	JX ALTA™ PRIME
Basis weight, gsm		ASTM D 3776	72
Thickness, mils		ASTM D 3776	8
Water Resistance, cm		AATCC 127	Pass
1" tensile, lbs	MD	ASTM D 882	38
	CD		30
Trapezoid Tear, lbs	MD	ASTM D-1117	14
	CD		13
MVTR	Perms	ASTM E-96, method A	> 5
Drainage Efficiency test		ASTM - 2273	>95%

Roll Dimensions (ft.)	W x L	9' X 100'	9' X 150'
		10' X 100'	10' X 150'

The information contained herein is furnished without charge or obligation and the recipient assumes all responsibility for its use. Because conditions of use and handling may vary and are beyond our control, we make no representation about, and are not responsible or liable for, the accuracy or reliability of said information or the performance of any product. Any specifications, properties or applications listed herein are provided as information only and in no way modify, amend, enlarge or create any warranty. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent. CLAF® is a registered trademark of JX Nippon ANCI Corporation.

08/15