



ALTA®

Commercial Breathable Housewrap

Properties Data Sheet

ESR - #1108

| Physical Properties | | Test Method | ALTA® Commercial |
|---------------------------|-------|---------------------|---------------------|
| Basis weight, gsm | | ASTM D 3776 | 82 |
| Thickness, mils | | ASTM D 3776 | 8 |
| Gurley Air Porosity, sec. | | TAPPI T-460 | > 2000 |
| Water Resistance, cm | | AATCC 127 | > 300 |
| 1" tensile, lbs | MD | ASTM D 882 | 30 |
| | CD | | 30 |
| Trapezoid Tear, lbs | MD | ASTM D-1117 | 13.5 |
| | CD | | 12.5 |
| MVTR | Perms | ASTM E-96, method A | 35 |
| UV Light Exposure | | Aging Test | 180 days |
| Drainage Efficiency test | | ASTM - 2273 | > 95% |
| Flammability | | ASTM - E-84 | Class A |

Roll Dimensions (ft.)

W x L

9' X 100'

9' X 150'

10' X 100'

10' X 150'

The information contained herein is furnished without charge or obligation and the recipient assumes all responsibility for its use. Because conditions of use and handling may vary and are beyond our control, we make no representation about, and are not responsible or liable for, the accuracy or reliability of said information or the performance of any product. Any specifications, properties or applications listed herein are provided as information only and in no way modify, amend, enlarge or create any warranty. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent. CLAF® is a registered trademark of ANCI, Inc.

0102-02/16